

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 911 149 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
28.04.1999 Bulletin 1999/17

(51) Int Cl.⁶: B32B 27/06, B32B 27/36

(21) Application number: 98308365.0

(22) Date of filing: 14.10.1998

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

- Cangiano, Dominick
Neshanic, New Jersey 08853 (US)
- Provino, Vincent J.
Clifton, New Jersey 07013 (US)
- Xu, Wayne
Lake-Hiawatha, New Jersey 07034 (US)

(30) Priority: 20.10.1997 US 954997

(71) Applicant: Hoechst Celanese Corporation
Warren, NJ 07059 (US)

(74) Representative:
De Minville-Devaux, Ian Benedict Peter et al
CARPMAELS & RANSFORD
43, Bloomsbury Square
London WC1A 2RA (GB)

(72) Inventors:
• Kuder, James E.
Fanwood, New Jersey 07023 (US)

(54) **Adhesives for making multilayer films comprising liquid crystalline polymers and poly(ethylene terephthalate) or polycarbonate**

(57) Multilayer films that include a thermotropic liquid crystalline polymer film layer and a poly(ethylene terephthalate) or polycarbonate film layer are bound together using a hot melt adhesive. Which may be either

(1) a blend of poly(α -olefins) that includes isotactic polypropylene, a polymer of a second lower poly(α -olefin), and a small amount of a higher poly(α -olefin); or (2) a polyamide-based hot melt adhesive.

EP 0 911 149 A2

Description**Related Applications**

- 5 [0001] The following four copending applications filed on even date herewith, all contain related subject matter US Application Serial Numbers: 08/_____, 08/_____, 08/_____, and 08/_____.

Field of the Invention

- 10 [0002] This invention relates to multilayer films, and more specifically to multilayer films that include a liquid crystalline polymer film and an isotropic polymer film, where the isotropic polymer is polycarbonate or poly(ethylene terephthalate).

Background of the invention

- 15 [0003] Liquid crystalline polymer (LCP) films have properties that are very desirable, such as excellent chemical resistance, high strength, and excellent gas barrier properties. However, these same films have certain undesirable properties. They often have poor transverse mechanical properties (i.e. they are strong in the machine direction, but tear easily in the direction transverse to the machine direction). It is also difficult to write or print on the films. LCP films are more expensive than conventional polymer films, such as polyester films.
- 20 [0004] It would be desirable to make multilayer films having LCP film bonded to one or more other films to obtain a film having the best properties of all of the various layers, such as a multilayer film having good gas barrier properties and relatively low cost.
- 25 [0005] However, LCP films do not bond well to each other or to other films by use of an adhesive. Their surfaces do not in general adhere to adhesives. There are thus very few examples of multilayer films containing one or more LCP layers. Multilayer films in which LCP's are bound to either poly(ethylene terephthalate) or polycarbonate using an adhesive appear to have been mentioned only rarely or not at all. An example of a multilayer film containing an LCP and another polymer is found in Japanese Patent Application No. 02-253,950, published in 1990, where a poly(butylene terephthalate) film layer is bound to VECTRA® A900 LCP film using a glycidyl-modified ethylene vinyl acetate adhesive. The other side of the VECTRA film is bound to polypropylene film by using two adhesive layers, a glycidyl-modified
- 30 ethylene vinyl acetate layer in contact with the LCP and an ethyl acrylate-ethylene-maleic anhydride copolymer in contact with the polypropylene. Japanese Patent publications 02-253,951 (1990) and 04-135,750 (1992) use similar adhesives for binding an LCP to poly(butylene terephthalate) and polypropylene. The latter of these patent applications also uses a saponified ethylene-vinyl acetate copolymer as an adhesive. Other publications that discuss multilayer films comprising an LCP barrier layer include Japanese Patent Publication 02-307,751 (1990), PCT Patent Publication
- 35 WO 95/23180, and European Patent Application No. 763,423.

Summary of the Invention

- 40 [0006] Adhesives have now been identified that bind LCP films having several different compositions to poly(ethylene terephthalate) and to polycarbonate. These adhesives are all hot melt adhesives and are the same for LCP bound to either poly(ethylene terephthalate) or polycarbonate. These are summarized below:

- 45 (1) A polyolefin blend, which is a mixture of poly(α -olefins), comprised mainly of isotactic polypropylene and a polymer of a second lower α -olefin, with small amounts of higher poly(α -olefins).
- (2) Polyamide resins of varying structure and molecular weight, including polyamides based on polymers of dimer acid.

- 50 [0007] Multilayer films are made by heating the two films that are being bonded together to a temperature above the melting points of both polymers and of the hot melt adhesive, under a compressive force, or by co-extruding the molten polymers including adhesives, to form multilayer films.

- [0008] The adhesives described above also turn out to be compatibilizers for blends of LCP and either polycarbonate or poly(ethylene terephthalate). The blends are made by extruding the LCP, polycarbonate or poly(ethylene terephthalate), and the adhesive/compatibilizer in the molten phase through an extruder under mixing conditions.

- 55 [0009] The words "films" and "sheets" and "films and sheets" are all used herein to describe thin flexible plastic fabricated structures. These generally have a thickness in the range of about 0.01 mm (0.4 mils) to about 10 mm (400 mils). This range of thicknesses is wide enough to encompass the common meaning of both films (< 0.25 mm) and sheets (thicker than films), and the words "films" and "sheets" therefore are used interchangeably to describe something

that may be described either as a film or sheet. The layers in coextruded films and sheets will likewise have the same broad range of thicknesses described above (i.e. about 0.01 mm to about 10 mm). The laminated and coextruded structures will be thicker since they are made up of several layers or films. Finally, "multilayer" sheets and films includes both laminated sheets and films and coextruded sheets and films. Laminated sheets and films are made by laminating sheets and films together. Coextruded sheets and films are made by coextruding the polymers through the die of an extruder in such a way that a multilayer film or sheet is formed. Multilayer films are also sometimes referred to as laminates, regardless of how they are made.

Detailed Description of the Invention

[0010] Liquid crystalline polymers (LCP's) are well known in the art and are characterized as having a liquid crystalline phase above the temperature at which the polymers become molten. The liquid crystalline polymers used in the multilayer films described herein are generally all-aromatic polymers, with relatively linear structures, which exhibit liquid crystalline behavior in the molten phase. They are generally polyesters or poly(ester-amides), and generally comprise monomer units that include within their structures, exclusive of functional groups, one or more of the following aromatic nuclei: 1,4-phenylene, 1,3-phenylene, 4,4'-biphenylene, and 2,6- and/or 2,7-naphthalene. Some LCP's also contain monomer units that are derived from ethylene glycol. Preferred LCP's contain only aromatic monomer units.

[0011] Generally, the LCP's comprise monomer units derived from one or more of the following monomers and generally at least two of the following monomers: terephthalic acid, isophthalic acid, 1,4-hydroquinone, resorcinol, 4-aminobenzoic acid, 4-hydroxybenzoic acid, 4-aminophenol, 1,4-phenylenediamine, 4,4'-biphenol, 4,4'-biphenyldicarboxylic acid, 6-hydroxy-2-naphthoic acid, 2,6-naphthalenedicarboxylic acid, and 2,6-dihydroxynaphthalene. Preferred LCP's include the polymers that are sold under the VECTRA® trademark, most of which comprise monomer units derived from 6-hydroxy-2-naphthoic acid (HNA) and 4-hydroxybenzoic acid (HBA) in their structure. Particularly preferred polymers from the VECTRA products are the VECTRA A polymers, made up of about 73% HBA monomer units and 27% HNA monomer units, and VECTRA E products, which contain HBA, HNA, 4,4'-biphenol (BP) and terephthalic acid (TA) as described in US Patent No. 4,473,682, incorporated herein by reference. The polyesteramide comprising HBA, HNA, BP, TA and 4-aminophenol, taught in US Patent No. 5,204,443, which is also incorporated herein by reference, is also useful with these adhesives. All of these products are available from Hoechst Technical Polymers, Summit, New Jersey. Another LCP which may be made into multilayer films using the adhesives taught herein is disclosed in U.S. Patent No. 5,656,714, incorporated herein by reference, and comprises monomer units derived from HBA, HNA, BP, TA, and resorcinol. LCP's comprising BP, HBA, TA, and other optional monomers are available from Amoco Chemicals under the XYDAR® trademark. LCP's containing 2,6-naphthalenedicarboxylic acid, BP, and other monomer units are also available from DuPont. All of these polymers can be made into multilayer films and polymer blends using the adhesives and methods taught herein.

[0012] The following LCP's were tested herein for the purpose of obtaining multilayer films:

- (1) VECTRA® A film, comprised of monomer units derived from HBA and HNA in a ratio of about 73/27, and having a melting temperature of about 280°C.
- (2) VECTRA® B Resin, which is a polyesteramide comprising monomer units derived from HNA, TA, and 4-aminophenol (see US Patent No. 4,330,457) and which has a melting temperature of about 280°C.
- (3) VECTRA® L Resin, which is a liquid crystalline poly(esteramide) comprised of monomer units derived from HBA, HNA, BP, TA and 4-aminophenol in accordance with US Patent No. 5,204,443. This resin has a melting temperature of 302°C.
- (4) An experimental LCP polyester, comprising monomer units derived from HBA, HNA, HQ, and TA, referred to hereinafter as Experimental Polymer 1. It has a melting temperature of about 220°C.
- (5) An experimental LCP polyester film that has been modified to have better adhesion by including monomer units that have sulfonate groups. It comprises monomer units made from about 73 mole % HBA, about 27 mole % HNA, and the sodium salt of 5-sulfisophthalic acid (0.2 mole %). It has a melting point of 270°C, and is further described in US Patent No. 5,227,456 which is incorporated herein by reference. It is referred to hereafter as Experimental Polymer 2.
- (6) An experimental liquid crystalline polymer that comprises monomer units derived from HBA, HNA, BP, TA, and resorcinol, as described in US Patent No. 5,656,714. It is referred to hereafter as Experimental Polymer 3.

[0013] Some of the polymers, e.g. VECTRA® A, B, and L resins are available commercially as glass-filled polymer resins or as films. VECTRA® A resin is available as fiber, film, or filled resin.

[0014] The polycarbonate and poly(ethylene terephthalate) films to which the LCP films are bound using the adhesives disclosed herein are all commercially available materials. Polycarbonate (the polycarbonate of bisphenol-A) and poly(ethylene terephthalate) are both commercially available resins that are widely used in various fabricated products,

including films. These polymers can be purchased in film form or purchased as resin and made into film.

[0015] The types of adhesives that are useful in this invention are all commercially available and are described in more detail below.

5 Polyolefin Blend

[0016] MACROMELT® Q5353 hot melt adhesive from Henkel Corporation turned out to be an excellent hot-melt adhesive for combining LCP films with polyethylene, polypropylene, polycarbonate, poly(ethylene terephthalate), and poly(phenylene sulfide). The material appears to be a mixture of poly(α -olefins), consisting mainly of isotactic polypropylene and a polymer of a second α -olefin, perhaps atactic poly(1-butene), combined with a small amount of one or more higher poly(α -olefin) oligomers. The material exhibits a trace of carbonyl absorption under infrared analysis, and traces of aromatic absorptions by C^{13} - NMR analysis, but both are at levels of < 3 mole %. The material is described in US Patent No. 5,512,625, which is incorporated herein by reference. The patent indicates that the polyolefin blend comprises an oligomer of an α -olefin with at least 8 carbon atoms in the monomer blended with a substantially amorphous poly(α -olefin) (perhaps atactic poly(1-butene) and a substantially crystalline poly(α -olefin) (e.g. isotactic polypropylene).

Polyamide Resins

[0017] A number of polyamide hot melt adhesives (individually, or together) are suitable for bonding polycarbonate film or poly(ethylene terephthalate film), to LCP films. These include the dimer acid based polyamide described below (MACROMELT® 6239) and other polyamides that are sold as hot melt adhesives (e.g. MACROMELT® 6211 and 6240), all of which generally have softening temperatures in the range of about 130°C to 160°C and application temperatures in the range of about 200°C - 270°C, depending on the melting temperatures and viscosities of the polymers being fabricated into multilayer films.

[0018] Dimer acid based polyamide adhesives are based on dimer acid, which is a mixture of dimers of C_{18} unsaturated fatty acids. The 36-carbon dimers are then polymerized with diamines to yield polyamides that are useful as hot melt adhesives. A dimer acid based polyamide that works well in this application is MACROMELT® 6239, supplied by Henkel Corporation. The material has a softening point (Ball and Ring) of 133°-143°C, a melt viscosity of 55-85 poise at 225°C, and an application temperature of 249° - 265°C. It is sold as an adhesive for ABS polymers and flexible vinyl polymers.

Methods of Making Laminated Films and Sheets

[0019] The films and sheets are most conveniently made on a large scale by a conventional coextrusion process in which the polymers that make up the various films and adhesive layers are combined within the die head in the molten phase, and extruded through a single slit to form a multilayer film. In coextrusion processes, the adhesives preferably have higher melt viscosities than adhesives used for compression bonding. The viscosities of the components in a coextrusion process should have comparable melt viscosities (within a factor of 10).

[0020] On a laboratory scale, samples of multilayer films are made by compression molding, i.e. by heating stacked layers of the films and the adhesive layers, which are also in film form, under pressure to a temperature above the melting point of the LCP and adhesive layers. Films that are to be laminated together generally have a thickness in the range of about 0.01 mm to about 10 mm.

[0021] The adhesives identified above are also suitable for use as compatibilizers in making polymer blends. The blends are made by conventional blending methods, most typically by feeding the polymers and adhesives simultaneously into an extruder and mixing them in the melt phase in the extruder. Twin screw extruders are generally preferred for making blends.

[0022] The practice of the invention is shown by the following examples, which are illustrative only and should not be viewed as limiting the scope of the invention.

Examples

Example 1. Synthesis of LCPs

[0023] The LCPs used in evaluating multilayer films were either commercially available or were made by methods similar to the method shown below for making a copolymer of about 73 mole % 4-hydroxybenzoic acid (HBA), 27% of 6-hydroxy-2-naphthoic acid (HNA), and 0.2% of 5-sulfoisophthalic acid (SSI).

[0024] A pilot scale reactor was charged with 150.4 lbs (493.8 moles) of HBA, 75.8 lbs (182.7 moles) of HNA, and

0.8 lbs (1.35 moles) of SSI. Following vacuum deaeration, acetic anhydride (154.3 lbs, 1.0 mole % excess) was charged into the reactor and the water in the cold finger condenser was turned on as an aid to control reflux. The mixture was then stirred at 45 rpm and heated according to the following temperature profile:

Stage	1	2	3	4	5	6	7	8	9	10	11	12
Final Temp (°C)	25	125	130	140	150	200	210	220	335	340	340	340
Time (min.)	1	50	10	40	20	45	5	7	115	10	10	360

[0025] After 7 to 8 hours the final temperature of 340°C was reached. The water in the cold finger was turned off when the reaction temperature reached 300°C. After holding at 340°C for 30 minutes, the vacuum stripping cycle was started during stage 12, and the stirring rate was reduced to 25 rpm. Full vacuum (7 mm Hg) was typically reached in 45 minutes. The mixture was heated at 340°C under full vacuum for an additional period of time to obtain the targeted stirring torque (base torque + 700 in.-lbs). After reaching the target torque the vacuum was broken by allowing nitrogen back into the reactor. The polymer was held at 340°C while it was extruded from the reactor through a 5 hole die with nitrogen pressure over 35-45 minutes. The polymer strands were cooled in a water trough and then sent through a chopper, and the reactor chip was collected in a drum. Samples for polymer evaluation were collected at the beginning, middle, and end of the extrusion. The polymer was tumble dried, sieved, and weighed. The typical yield was 154 pounds (77%).

Example 2. Sample Preparation and Testing

[0026] LCP films were prepared by extruding the LCP in the molten phase through a die with a vacuum applied at the venting port to remove volatiles. The extrusion line was a conventional pilot scale extrusion line, producing 2-mil thick LCP films. Poly(ethylene terephthalate) or polycarbonate and the adhesives were separated and made into films with dimensions of 16.5 cm x 21.5 cm x 1-1.5 mm thick by compression molding on a Wabash Compressor at a temperature of about 20°C above the melting point of the polymer.

[0027] For screening purposes, structures having two layers, either of LCP and adhesive or thermoplastic polymer and adhesive, are first made by heating the LCP or thermoplastic film on fluoropolymer coated aluminum foil in an oven to a temperature about 20°C above the melting temperature. After the polymer softens, the adhesive layer is placed on top, and then covered with a fluoropolymer coated aluminum release sheet and a 2-pound steel weight. The pressure of the weight is maintained for about 5 minutes, and then the heat and pressure are removed. The adhesive bonding of the thermoplastic or LCP to the adhesive is measured qualitatively as follows. The free ends of the two film layers in the test piece are grasped by hand and pulled apart. The force needed to pull them apart is rated qualitatively on a scale of "1" to "4", where "1" means that adhesion is poor, with no force being required to separate the layers, and "4" means excellent adhesion (the strips cannot be separated by hand). If the LCP and thermoplastic polymers bond well to the same adhesives, (i.e. are rated "3" or "4" using the same adhesive), then they are expected to also attach to each other using the same adhesives to form a multilayer film. The results of the tests are presented in Table 1.

[0028] Three layer films were made in some of the cases where it was predicted that good quality three-layer films can be made, based on the screening tests described above. Since good three-layer films were obtained in agreement with the predictions resulting from the screening tests, only a portion of the three layer films that were expected to have good adhesion were actually made. Three layer films are made by the following method.

[0029] A test strip of the LCP (about 2.54 cm x 15.24 cm x 2 mil) is placed on a fluoropolymer coated aluminum release sheet in an oven at a temperature approximately 20°C above the softening point of the LCP. When visual inspection indicates that the polymer has softened (typically 2-3 minutes), a 2.54 cm test strip of the candidate adhesive is placed on top of the softened polymer. An aluminum release sheet is placed on top of the adhesive and a 2 lb steel weight is set on top of the release sheet. After approximately 5 minutes the material is removed from the oven and allowed to cool to room temperature and the aluminum release sheet is removed. The thermoplastic layer is then applied by placing the LCP/adhesive structure within a 12.7 cm steel frame on top of an aluminum release sheet lying on the platen of a hot press machine set approximately 20°C above the melting temperature of the thermoplastic material. A 2.54 cm strip of thermoplastic polymer film is placed on top of the adhesive, and fluoropolymer coated aluminum release sheet is placed on top of the material. Two tons of pressure is applied for 10 minutes and then the pressure is released. The material is removed from the platen and allowed to cool to room temperature.

[0030] Quantitative measurements of the strengths of the bonds between the LCP and thermoplastic layers are carried out using a modified Simple Lap Joint Test, as set forth in ASTM test method D 1002-94. The test is really designed for bonded metal specimens, but is suitable for comparative testing of bonded polymer films. Samples of 4 mm thick multilayer films are prepared with 1/2" of overlap for testing. The films are pulled apart using an Instron tensile

tester with an angle of peel of 0°. These samples exhibit levels of adhesion between the layers that are comparable to the adhesion between layers in commercial samples of multilayer films (high density polyethylene and ethylene vinyl alcohol) that are used in automobile fuel tanks.

5 Example 3. Coextrusion of a Multilayer Film:

[0031] Multilayer films are coextruded using a pilot line designed for making multilayer films. The pilot line has three extruders with screw diameter of 3.5, 2.0 and 1.5 inches. The polymeric material having the greatest total thickness in the coextruded film is generally extruded with the extruder having the largest screw diameter. The molten polymer streams are delivered to the feed block in channels in which the streams are divided and then combined again so that they emerge from the die lips as a multilayer film, which then impinges on a chill roll and is finally taken up on a roll winder. During the extrusion the overall thickness of the extruded film is continuously monitored by a beta gauge. By means of this equipment, several multilayer films are produced, having the following 5-layer structure:

15 Polycarbonate or poly(ethylene terephthalate) (PET) 3 mils
 Adhesive, 1 mil
 LCP, 2 mils
 Adhesive 1 mil
 Polycarbonate or PET, 3 mils

20 [0032] The LCP is Experimental Polymer 3, which is a copolymer of 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, terephthalic acid, 4,4'-biphenol, and resorcinol, as described in US Patent No. 5,656,714. The polycarbonate and PET are commercially available materials having a molecular weight suitable for making films. The adhesive is MACROMELT Q5353.

25 Example 4. Adhesion of Polyolefin Blend to Polycarbonate and Poly(ethylene terephthalate) (PET)

[0033] MACROMELT® Q5353 polyolefin blend showed good adhesion to all of the conventional polymers that were tested (HDPE, polypropylene, polycarbonate, poly(phenylene sulfide), and PET), achieving a score of 4 with all of the polymer films using the qualitative test method for adhesion. It also adhered well to all of the LCP's that were tested, except VECTRA® B resin, where it still had acceptable adhesion (score of 3) (see Table 1). It is thus the one adhesive tested that was good for making multilayer films of polycarbonate, PET, polyethylene, polypropylene, poly(phenylene sulfide) and LCP's in any order or combination. It is truly surprising that this material could be a "universal adhesive" for multilayer films of conventional polymers and LCP's.

35 Example 5. Adhesion of Polyamide Adhesives to LCP Polycarbonate and PET

[0034] Several polyamide-based hot melt adhesives adhere well to LCP's, polycarbonate and PET, and are thus expected to be useful for making multilayer films. MACROMELT® 6239, 6211, and 6240 all adhere well to polycarbonate and PET film (score of 4 using the qualitative test) and adhere well or acceptably well to all of the LCP's that were tested (see Table 1). These are therefore expected to bind polycarbonate or PET to LCP's to make multilayer films.

Compatibilization Tests

45 [0035] The adhesives for making multilayer films also act as compatibilizers for making blends of the same polymers that the adhesives bind together. PET or polycarbonate can be blended with LCP's similarly to the way polypropylene is blended with LCP's, as follows.

[0036] As an example, a blend of a fiber grade polypropylene (Montell type KY 6100) with Experimental Polymer 1 was made and evaluated as follows. The blends contained 10% by weight LCP and 90% by weight polypropylene. In addition, an antioxidant (NAUGUARD™ 10 from Ciba-Geigy) and an additive which is a compatibilizer for some combinations of polymers but is not an effective compatibilizer for polypropylene and LCP's (NUCREL™ 0903 ethylene-methacrylic acid copolymer from DuPont) were included at levels of 0.2% and 0.5% by weight respectively for all the samples that were tested. The combinations were compounded with compatibilizers disclosed herein by a single or double pass through an extruder. The compounds were cast into film. The films that included these compatibilizers had a better, more uniform appearance than the films that did not include the compatibilizers.

55 [0037] The compounds were also made into films by extrusion, and the tensile properties were measured by ASTM method D1876. The results for the control (without the compatibilizer) and the two samples with the compatibilizer follow:

- (1) No compatibilizer - tensile modulus, 1.44 GPa; yield stress, 22.5 MPa;
 (2) 1% by weight of a 50:50 blend of POLYBOND® 3002 and MACROMELT® 6239 - tensile modulus, 1.69 GPa; yield stress, 29.5 MPa;
 (3) 1% by weight of a 40:60 blend of POLYBOND® 3002 and MACROMELT® 6239 - tensile modulus, 1.85 GPa; yield stress, 29.9 MPa.

[0038] LCP's and either polycarbonate or PET in the adhesives taught herein behave similarly to the example above. Thus, the blends that include the compatibilizers taught herein have improved appearance and improved tensile properties compared with blends without the compatibilizers.

[0039] It is to be understood that the above-described embodiments of the invention are illustrative only and that modification throughout may occur to one skilled in the art. Accordingly this invention is not to be regarded as limited to the embodiments disclosed herein.

Table 1.

BOND STRENGTH ¹ BETWEEN LCP'S, POLYCARBONATE, POLY(ETHYLENE TEREPHTHALATE), AND ADHESIVES				
LCP	MACROMELT® Q5353	MACROMELT® 6239	MACROMELT® 6211	MACROMELT® 6240
VECTAR® A	4	4	4	4
VECTAR® B	3	3	3	3
VECTAR® L	4	4	4	3
EXPERIMENTAL POLYMER 1	4	4	4	4
EXPERIMENTAL POLYMER 2	4	4	4	4
EXPERIMENTAL POLYMER 3	4	4	.(2)	.(2)
POLY(ETHYLENE TEREPHTHALATE)	4	4	.(2)	.(2)
POLYCARBONATE	4	4	4	4

¹ Scale of 1-4; 4 is good, 3 is acceptable, and 1 and 2 are not acceptable

² Not tested.

Claims

1. A multilayer film, comprising a layer comprised of polycarbonate or poly(ethylene terephthalate), a thermotropic liquid crystalline polymer layer, and a hot melt adhesive layer between said layers, wherein said hot melt adhesive is selected from the group consisting of (1) a polyolefin blend; and (2) a polyamide.
2. The multilayer film as recited in Claim 1, wherein said hot melt adhesive is selected from the group consisting of (1) a polyolefin blend comprising a substantially crystalline first poly(α -olefin), a substantially amorphous second poly(α -olefin), and an oligomer of a third α -olefin, which has at least 8 carbon atoms in the α -olefin monomer and (2) a polyamide having an application temperature of about 200° to about 270°C and a softening temperature in the range of about 130° to about 160°C.
3. The multilayer film as recited in Claim 1, wherein said hot melt adhesive is a polyolefin blend comprising isotactic polypropylene, a substantially amorphous second poly(α -olefin), and an oligomer of a third α -olefin which has at least 8 carbon atoms in the α -olefin monomer.
4. The multilayer film as recited in Claim 1, wherein said hot melt adhesive is MACROMELT® Q5353.
5. The multilayer film as recited in Claim 1, wherein said hot melt adhesive is a dimer acid based polyamide having a softening temperature in the range of about 133°C to about 143°C, and a melt viscosity of about 55 poise to

about 85 poise, measured at 225°C.

6. The multilayer film as recited in Claim 1, wherein said hot melt adhesive is a polyamide selected from the group consisting of MACROMELT® 6239, MACROMELT 6211, and MACROMELT 6240.
7. The multilayer film as recited in Claim 1, wherein said thermotropic liquid crystalline polymer film comprises a polymer derived from one or more monomers selected from the group consisting of terephthalic acid, isophthalic acid, 1,4-hydroxyquinone, resorcinol, 4-aminobenzoic acid, 4-hydroxybenzoic acid, 4-aminophenol, 1,4-phenylenediamine, 4,4'-biphenol, 4,4'-biphenyldicarboxylic acid, 6-hydroxy-2-naphthoic acid, 2,6-naphthalenedicarboxylic acid, and 2,6-dihydroxynaphthalene.
8. The multilayer film as recited in Claim 1, wherein said thermotropic liquid crystalline polymer film is made from a thermotropic liquid crystalline polymer selected from the group consisting of (1) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid and 6-hydroxy-2-naphthoic acid; (2) a polymer that consists essentially of monomer units derived from 6-hydroxy-2-naphthoic acid, terephthalic acid, and 4-aminophenol; (3) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, 4,4'-biphenol, terephthalic acid, and 4-aminophenol; (4) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, hydroquinone, and terephthalic acid; (5) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, and 5-sulfoisophthalic acid; (6) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, 4,4'-biphenol, terephthalic acid, and resorcinol; and (7) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, terephthalic acid, and 4,4'-biphenol.
9. A multilayer film as recited in Claim 1, wherein said thermotropic liquid crystalline polymer layer, said layer comprised of polycarbonate or poly(ethylene terephthalate), and said hot melt adhesive layer each have a thickness in the range of about 0.01 mm to about 10 mm.
10. A method of laminating a thermotropic liquid crystalline polymer film and a film comprised of polycarbonate or poly(ethylene terephthalate) together, wherein said thermotropic liquid crystalline polymer film and said film comprised of polycarbonate or poly(ethylene terephthalate) are heated under a compressive force with a hot melt adhesive between said thermotropic liquid crystalline polymer film and said film comprised of polycarbonate or poly(ethylene terephthalate) to a temperature above the melting points of said thermotropic liquid crystalline polymer film, said film comprised of polycarbonate or poly(ethylene terephthalate), and said hot melt adhesive for a time sufficient to melt said hot melt adhesive and bind said film comprised of polycarbonate or poly(ethylene terephthalate) and said thermotropic liquid crystalline polymer film to one another to yield a laminated film.
11. The method as recited in Claim 10, wherein said hot melt adhesive is in the form of a film.
12. The method as recited in Claim 10, wherein said thermotropic liquid crystalline polymer film and said film comprised of polycarbonate or poly(ethylene terephthalate) each have a thickness in the range of about 0.01 mm to about 10 mm.
13. The method as recited in Claim 10, wherein said hot melt adhesive is selected from the group consisting of: (1) a polyolefin blend; and (2) a polyamide.
14. The method as recited in Claim 10, wherein said hot melt adhesive is selected from the group consisting of: (1) a polyolefin blend comprising a substantially crystalline first poly(α -olefin), a substantially amorphous second poly(α -olefin), and an oligomer of a third α -olefin, which has at least 8 carbon atoms in the α -olefin monomer; and (2) a polyamide having an application temperature of about 200° to about 270°C and a softening temperature in the range of about 130° to about 160°C.
15. The method as recited in Claim 10, wherein said hot melt adhesive is a polyolefin blend comprising isotactic polypropylene, a substantially amorphous second poly(α -olefin), and an oligomer of a third α -olefin, which has at least 8 carbon atoms in the α -olefin monomer.
16. The method as recited in Claim 10, wherein said hot melt adhesive is MACROMELT® Q5353.

17. The method as recited in Claim 10, wherein said hot melt adhesive is a polyamide selected from the group consisting of MACROMELT® 6239, MACROMELT 6211, and MACROMELT 6240.
18. The method as recited in Claim 10, wherein said thermotropic liquid crystalline polymer film comprises a polymer derived from one or more monomers selected from the group consisting of terephthalic acid, isophthalic acid, 1,4-hydroquinone, resorcinol, 4-aminobenzoic acid, 4-hydroxybenzoic acid, 4-aminophenol, 1,4-phenylenediamine, 4,4'-biphenol, 4,4'-biphenyldicarboxylic acid, 6-hydroxy-2-naphthoic acid, 2,6-naphthalenedicarboxylic acid, and 2,6-dihydroxynaphthalene.
19. The method as recited in Claim 10, wherein said thermotropic liquid crystalline polymer film is made from a thermotropic liquid crystalline polymer selected from the group consisting of (1) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid and 6-hydroxy-2-naphthoic acid; (2) a polymer that consists essentially of monomer units derived from 6-hydroxy-2-naphthoic acid, terephthalic acid, and 4-aminophenol; (3) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, 4,4'-biphenol, terephthalic acid, and 4-aminophenol; (4) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, hydroquinone, and terephthalic acid; (5) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, and 5-sulfisophthalic acid; (6) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, 4,4'-biphenol, terephthalic acid, and resorcinol; and (7) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, terephthalic acid, and 4,4'-biphenol.
20. A method of making a multilayer film that comprises a layer comprised of polycarbonate or poly(ethylene terephthalate) and a thermotropic liquid crystalline polymer layer bound to one another, wherein said thermotropic liquid crystalline polymer, said polycarbonate or poly(ethylene terephthalate), and a hot melt adhesive are combined in the molten state in a die head and extruded through a single slit to yield a multilayer film.
21. The method as recited in Claim 20, wherein said hot melt adhesive is selected from the group consisting of (1) a polyolefin blend; and (2) a polyamide.
22. The method as recited in Claim 20, wherein said hot melt adhesive is selected from the group consisting of: (1) a polyolefin blend comprising a substantially crystalline first poly(α -olefin), a substantially amorphous second poly(α -olefin), and an oligomer of a third α -olefin, which has at least 8 carbon atoms in the α -olefin monomer and (2) a polyamide having an application temperature of about 200° to about 270°C and a softening temperature in the range of about 130° to about 160°C.
23. The method as recited in Claim 20, wherein said hot melt adhesive is a polyolefin blend comprising isotactic polypropylene, a substantially amorphous second poly(α -olefin), and an oligomer of a third α -olefin, which has at least 8 carbon atoms in the α -olefin monomer.
24. The method as recited in Claim 20, wherein said hot melt adhesive is MACROMELT® Q5353.
25. The method as recited in Claim 20, wherein said hot melt adhesive is a polyamide selected from the group consisting of MACROMELT® 6239, MACROMELT 6211, and MACROMELT 6240.
26. The method as recited in Claim 20, wherein said thermotropic liquid crystalline polymer film comprises a polymer derived from one or more monomers selected from the group consisting of terephthalic acid, isophthalic acid, 1,4-hydroquinone, resorcinol, 4-aminobenzoic acid, 4-hydroxybenzoic acid, 4-aminophenol, 1,4-phenylenediamine, 4,4'-biphenol, 4,4'-biphenyldicarboxylic acid, 6-hydroxy-2-naphthoic acid, 2,6-naphthalenedicarboxylic acid, and 2,6-dihydroxynaphthalene.
27. The method as recited in Claim 20, wherein said thermotropic liquid crystalline polymer film is made from a thermotropic liquid crystalline polymer selected from the group consisting of (1) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid and 6-hydroxy-2-naphthoic acid; (2) a polymer that consists essentially of monomer units derived from 6-hydroxy-2-naphthoic acid, terephthalic acid, and 4-aminophenol; (3) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, 4,4'-biphenol, terephthalic acid, and 4-aminophenol; (4) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, hydroquinone, and terephthalic acid; (5) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, and 5-sulfisophthalic acid; (6) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, 4,4'-biphenol, terephthalic acid, and resorcinol; and (7) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, terephthalic acid, and 4,4'-biphenol.

5 ymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, and 5-sulfoisophthalic acid; (6) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, 4,4'-biphenol, terephthalic acid, and resorcinol; and (7) a polymer that consists essentially of monomer units derived from 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, terephthalic acid, and 4,4'-biphenol.

- 10 28. A compatibilized polymer blend, comprising poly(ethylene terephthalate) or polycarbonate, a thermotropic liquid crystalline polymer, and a hot melt adhesive, wherein said hot melt adhesive is selected from the group consisting of a polyolefin blend and a polyamide.

15

20

25

30

35

40

45

50

55

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 911 149 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
21.07.1999 Bulletin 1999/29

(51) Int Cl⁸: **B32B 27/06, B32B 27/36**

(43) Date of publication A2:
28.04.1999 Bulletin 1999/17

(21) Application number: 98308365.0

(22) Date of filing: 14.10.1998

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

- Canglano, Dominick
Neshanic, New Jersey 08853 (US)
- Provino, Vincent J.
Clifton, New Jersey 07013 (US)
- Xu, Wayne
Lake-Hiawatha, New Jersey 07034 (US)

(30) Priority: 20.10.1997 US 954997

(71) Applicant: Hoechst Celanese Corporation
Warren, NJ 07059 (US)

(74) Representative:
De Minville-Devaux, Ian Benedict Peter et al
CARPMAELS & RANSFORD
43, Bloomsbury Square
London WC1A 2RA (GB)

(72) Inventors:
• Kuder, James E.
Fanwood, New Jersey 07023 (US)

(54) **Adhesives for making multilayer films comprising liquid crystalline polymers and poly(ethylene terephthalate) or polycarbonate**

(57) Multilayer films that include a thermotropic liquid crystalline polymer film layer and a poly(ethylene terephthalate) or polycarbonate film layer are bound together using a hot melt adhesive, Which may be either

(1) a blend of poly(α -olefins) that includes isotactic polypropylene, a polymer of a second lower poly(α -olefin), and a small amount of a higher poly(α -olefin); or (2) a polyamide-based hot melt adhesive.

EP 0 911 149 A3

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 8365

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP 0 503 063 A (DAICEL CHEM) 16 September 1992 * page 14, line 44 - line 56 * * page 12, line 7 - line 8 *	10, 11, 18-20, 26, 27	832B27/06 832B27/36
A	* page 4, line 12 - page 5, line 24 * * claims 1, 18-20, 23, 28, 32 * * page 12, line 4 - line 6 * * page 12, line 28 - line 41 * * page 14, line 41 - line 43 * -----	1-9, 12-17, 21-25	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			832B C09J
-The present search report has been drawn up for all claims-			
Place of search THE HAGUE		Date of completion of the search 28 January 1999	Examiner Girard, S
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons S : member of the same patent family, corresponding document	

EPO FORM 1503 (3.82) (Rev.01)



European Patent
Office

Application Number
EP 98 30 8365

CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

- ☐ Only part of the claims have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid, namely claim(s):
- ☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

see sheet B

- ☐ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.
- ☐ As all searchable claims could be searched without effort justifying an additional fee, the Search Division did not invite payment of any additional fee.
- ☐ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid, namely claims:
- ☒ None of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims, namely claims:

1-27



European Patent
Office

LACK OF UNITY OF INVENTION
SHEET B

Application Number
EP 98 30 8365

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

1. Claims: 1-27

Multilayered product comprising a layer of polyethylene terephthalate or polycarbonate resin, a hot melt adhesive layer and a layer of thermotropic liquid crystalline polymer.

2. Claim : 28

A compatibilized polymer blend comprising polyethylene terephthalate or polycarbonate, a thermotropic liquid crystalline polymer and a hot melt adhesive.

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 98 30 8365

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

28-01-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0503063 A	16-09-1992	WO 9205954 A US 5364669 A	16-04-1992 15-11-1994

EPO FORM 94015

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82